

FIELD OF THE INVENTION

BACKGROUND OF THE INVENTION

[0003] The felt is adapted to pass through the pressing stages of the machine to effect drainage of water from the paper web. It must also pass

through the pressing stage of a cleaning apparatus. Each time it passes through a pressing stage, the felt is subjected to compression. However, in spite of the stresses imparted to the felt by the pressing stages, it is necessary to retain the resilient character of the felt in order to maintain its water permeability.

[0004] With the recent introduction of high speed papermaking machines, the time span from the passage of the felt through a first pressing stage in the machine to a next pressing stage has become relatively short (approximately one second). As a result, the time allowed for restoration of the felt to its three dimensional structure as a result of its own resiliency has become very short. The nip pressure at the pressing stages has also increased. Because of the foregoing conditions, a dimensional change in the felt becomes inevitable, with the adverse effect that the felt loses its stability while running, and exhibits a deterioration in its water-squeezing capability within a few days, even though it is expected to have a service life of about 40 days.

[0005] The principal object of the invention is to solve the above-mentioned problem, and to offer a papermaking felt which can retain its three-dimensional character even in a high speed papermaking machine in which the felt is subjected to compression repeatedly in a short time period.

[0006] The papermaking felt in accordance with the invention comprises a ground fabric layer composed of a woven fabric, and a fibrous web placed on at least one side of the ground fabric layer, the

[0011] FIG. 2(b) is a similar view showing another embodiment, in which the structure of the ground fabric layer is changed;

[0012] FIG. 3(a) is a schematic, enlarged, sectional view of another embodiment of a felt according to the invention, comprising a woven ground fabric layer wherein straight yarns are added to the warp or weft; and

[0013] FIG. 3(b) is a similar view showing another embodiment, in which the structure of the ground fabric layer is changed.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0014] Briefly, in FIGS. 1(a) and 1(b), the ground fabric layer of the felt is a woven fabric of double weave construction, and a part of the warp or weft is composed of straight yarns. Likewise, in the multiple weave construction illustrated in FIGS. 2(a) and 2(b), a part of the warp or weft consists of straight yarns. In FIGS. 3(a) and 3(b), straight yarns are added to the warp or weft of the ground fabric layer.

[0015] The felt 1 of the invention is composed of fibrous webs 3 accumulated on a ground fabric layer 2 which comprises a woven fabric. A fibrous web 3 may be placed on only one side of the ground fabric layer 2, or, alternatively, fibrous webs may be placed both on the top and on the bottom of the ground fabric layer. The fibrous web or webs are intertwined with the ground fabric layer by needling and are thereby made integral with the ground fabric layer. Markings generated by the needling process are not shown in the drawings.

K with a predetermined orientation by heat sealing (i.e., by lamination) or by an adhesive.

[0018] In the drawings, a circle within circle denotes a straight yarn in the warp direction, and a single circle denotes a winding yarn in the warp direction. A pair of parallel lines indicates a straight yarn in the weft direction, a pair of parallel lines with dots between them denotes a winding yarn in the weft direction.

[0019] In the ground fabric layer 2 shown in the drawings, straight yarns S are present in both the warp and weft directions. Therefore, dimensional stability is obtained in both directions, that is, in the MD direction as well as in the CMD direction. But, needless to say, similar dimensional stability is obtainable even if the straight yarns are used only in one direction, that is, only in the warp direction or only in the weft direction. For instance, the modulus in the weft direction is improved when straight yarns S are inserted in the ground fabric layer 2 in the weft direction, with a resultant smaller size reduction occurring as a result of the heat setting during manufacture. The straight yarns S suppress the increase in width and reduction of thickness that occur during use, resulting in a stable dimension in the sideward direction.

[0020] When the ground fabric layer 2 is composed of a weft double or a weft triple weave, the straight yarns S are inserted in the warp direction and when the ground fabric layer 2 is composed of a warp double or warp triple weave, the straight yarns S are inserted in the weft direction. It has

been confirmed that the product so produced is dimensionally stable in both the warp and weft directions in use. This felt construction is particularly useful for improving the dimensional stability of papermaking felts used in recently introduced high speed papermaking machines.

[0021] The "straight yarn" S includes a yarn which is inherently straight, such as PET (polyethylene terephthalate) monofilaments. "Straight yarn" also includes those yarns which are "straight" in relation to the winding yarns K. For instance, when the winding yarns K are elastic, flexible yarns, such as nylons, then the less flexible monofilaments or multifilaments of PBT, PPS, nylon 610, nylon 612, nylon 12, semi-aromatic nylon (MXD6), or aramid are selected as the straight yarns. Also, the straight yarns are not necessarily limited to those intended to be straight, but include those yarns which become nearly straight as result of the fabric structure formation, because "straightness" may be determined relatively as mentioned above.

[0022] The "winding" yarn K means the yarn which plays the role of anchoring, or undulating up and down relative to the straight yarns S in the cases of FIGs. 1(a), 1(b), 2(a) and 2(b). And, in case of FIGs. 3(a) and 3(b), the winding yarn K is the essential yarn which composes the ground fabric structure.

[0023] To summarize the advantages of the invention, as mentioned above, the invention is a paper-making felt comprising a ground fabric layer of a woven fabric and a fibrous web placed on at

least one side of said ground fabric layer, the ground fabric layer and fibrous web being intertwined and made integral by needling.

[0024] According to one aspect of the invention, the felt is characterized in that all yarns of either the warp or weft forming the ground fabric layer are straight yarns, or a part of the distributed yarns of the warp or weft are straight yarns. Owing to the dimensional stability of the straight yarns of the warp or weft comprising the ground fabric layer, the modulus in the direction of the inserted straight yarns is improved. Consequently, the width decrease that occurs in the heat-setting stage of the manufacturing process decreases, and the increase in width and decrease in thickness during use of the felt in a papermaking machine are suppressed. Thus, the invention contributes to the stability of the felt, while running in the papermaking machine, with decreased elongation in the longitudinal and sideward directions. The papermaking felt of the invention is capable of satisfactorily performing its desired function as a papermaking felt for a longer time, which is a highly desirable and advantageous effect.

[0025] According to another aspect of the invention, the papermaking felt is characterized in that the ground fabric layer is composed of winding yarns, and straight yarns are additionally and evenly inserted along the warp or weft of the ground fabric yarn. Because the ground fabric layer may be reinforced with straight yarns, the dimensional stability of the ground fabric layer

may be obtained relatively easily, which is also a highly desirable and advantageous effect.

10590-0520-1